



Amendments to the Claims

1. (Previously presented) An organotellurium compound represented by the formula (1)




wherein R^1 is C_1 - C_8 alkyl, R^2 and R^3 are each a hydrogen atom or C_1 - C_8 alkyl, and R^4 is aryl, substituted aryl, aromatic heterocyclic group, hydroxycarbonyl or cyano, provided that R^2 and R^3 are not simultaneously a hydrogen atom.

2. (Previously presented) A process for preparing an organotellurium compound of the formula (1) comprising reacting a compound of the formula (2), a compound of the formula (3) and metallic tellurium



wherein R^1 is C_1 - C_8 alkyl, R^2 and R^3 are each a hydrogen atom or C_1 - C_8 alkyl, and R^4 is aryl, substituted aryl, aromatic heterocyclic group, hydroxycarbonyl or cyano, provided that R^2 and R^3 are not simultaneously a hydrogen atom




wherein R^2 , R^3 and R^4 are as defined above, and X is a halogen atom



wherein R^1 is as defined above, M is an alkali metal, alkaline earth metal or copper atom, and m is 1 when M is an alkali metal, m is 2 when M is an alkaline earth metal, or m is 1 or 2 when M is a copper atom.

3. (Cancelled)

4. (Previously presented) A living radical polymerization initiator of the formula (4)



wherein R^5 is C_1 - C_8 alkyl, aryl, substituted aryl or aromatic heterocyclic group, R^2 and R^3 are each a hydrogen atom or C_1 - C_8 alkyl, and R^4 is aryl, substituted aryl, aromatic heterocyclic group, hydroxycarbonyl or cyano, provided that R^2 and R^3 are not simultaneously a hydrogen atom.

5. (Withdrawn) A process for producing a living radical polymer characterized by polymerizing a vinyl monomer with use of a compound of the formula (4) as a living radical polymerization initiator.


6. (Withdrawn) A living radical polymer which is obtainable by subjecting a vinyl monomer to living radical polymerization with use of a living radical polymerization initiator of the formula (4).

7. (Withdrawn) A macro living radical polymerization initiator comprising the living radical polymer of claim 6.

8. (Withdrawn) A process for producing a block copolymer comprising polymerizing a vinyl monomer using the macro living radical polymerization initiator of claim 7 as a living radical polymerization initiator.


9. (Withdrawn) A block copolymer which is obtainable by polymerizing a vinyl monomer using the macro living radical polymerization initiator of claim 7 as a living radical polymerization initiator.

10. (Previously presented) An organotellurium compound as defined in claim 1, represented by the formula (5)



wherein R^1 is C_1 - C_8 alkyl, R^2 and R^3 are each a hydrogen atom or C_1 - C_8 alkyl, and R^4 is cyano, provided that R^2 and R^3 are not simultaneously a hydrogen atom.

11. (Previously presented) A living radical polymerization initiator as defined in claim 4, represented by the formula (6)



wherein R^5 is C_1 - C_8 alkyl, aryl, substituted aryl or aromatic heterocyclic group, R^2 and R^3 are each a hydrogen atom or C_1 - C_8 alkyl, and R^4 is cyano, provided that R^2 and R^3 are not simultaneously a hydrogen atom.

12. (Withdrawn) A process for producing a living radical polymer as defined in claim 5 characterized by polymerizing a vinyl monomer with use of a compound of the formula (6) as a living radical polymerization initiator.

13. (Withdrawn) A living radical polymer as defined in claim 6 which is obtainable by subjecting a vinyl monomer to living radical polymerization with use of a living radical polymerization initiator of the formula (6).

14. (Withdrawn) A micro living radical polymerization initiator comprising the living radical polymer of claim 13.

15. (Withdrawn) A process for producing a block copolymer comprising polymerizing a vinyl monomer using the macro living radical polymerization initiator of claim 14 as a living radical polymerization initiator.

16. (Withdrawn) A block copolymer which is obtainable by polymerizing a vinyl monomer using the macro living radical polymerization initiator of claim 14 as a living radical polymerization initiator.

17. (Withdrawn) A macro living radical polymerization initiator for preparing a block copolymer comprising the living radical polymer of claim 6.

18. (Withdrawn) A process for producing a block copolymer comprising polymerizing a vinyl monomer using the macro living radical polymerization initiator for preparing a block copolymer of claim 7 as a living radical polymerization initiator.

19. (Withdrawn) A block copolymer which is obtainable by polymerizing a vinyl monomer using the macro living radical polymerization initiator for preparing a block copolymer of claim 7 as a living radical polymerization initiator.

20. (Withdrawn) A macro living radical polymerization initiator for preparing a block copolymer comprising the living radical polymer of claim 13.

21. (Withdrawn) A process for producing a block copolymer comprising polymerizing a vinyl monomer using the macro living radical polymerization initiator for preparing a block copolymer of claim 14 as a living radical polymerization initiator.

22. (Withdrawn) A block copolymer which is obtainable by polymerizing a vinyl monomer using the macro living radical polymerization initiator for preparing a block copolymer of claim 14 as a living radical polymerization initiator.